


## Black Neoprene Sheet (25% Content)

Product Code: RC0332

### Product Description

Our black commercial neoprene sheet is a cost efficient material, which is suitable for use in a wide variety of medium range applications. We manufacture this product using a combination of neoprene rubber and SBR compound. This creates a product which provides many of the same physical properties as our premium grade materials at a significantly reduced cost.

### Technical Specification



Properties	Test Method	Values
Product	-	Commercial Neoprene Sheeting
Compound	-	CR / SBR
Hardness (Shore A)	ISO 7619-1	60° ± 5°
Density	ISO 2781	1.40 ± 0.05 g/cm <sup>2</sup>
Tensile Strength	ISO 37	3.5 N/mm <sup>2</sup>
Elongation at Break	ISO 37	250%
Tear Strength	ISO 34-1	12
Working Temperature Range	-	-20°C to + 80°C



The information contained on this product information sheet is to be used as guidance. The advice is given in good faith and does not constitute any guarantee or recommendation for suitability. The Rubber Company cannot be held liable for any damage caused by incorrect installation. We hereby reserve the right to change the technical information herewith without notification or prior agreement.

## Standard Sizes

Properties	Tolerances
1mm x 1.4m x 10m	+/- 0.2mm
1.5mm x 1.4m x 10m	+/- 0.3mm
3mm x 1.4m x 10m	+/- 0.3mm
4mm x 1.4m x 10m	+/- 0.4mm
5mm x 1.4m x 10m	+/- 0.4mm
6mm x 1.4m x 10m	+/- 0.5mm
8mm x 1.4m x 5m	+/- 0.7mm
10mm x 1.4m x 5m	+/- 1mm
15mm x 1.4m x 5m	+/- 1mm
20mm x 1.4m x 5m	+/- 1.4mm
25mm x 1.4m x 5m	+/- 1.75mm

## Made To Order Sizes - Subject To Minimum Order Quantities

Properties	Tolerances
0.5mm x 1.4m x 10m	+/- 0.2mm
32mm x 1m x 1m	-
38mm x 1m x 1m	-
40mm x 1m x 1m	-



The information contained on this product information sheet is to be used as guidance. The advice is given in good faith and does not constitute any guarantee or recommendation for suitability. The Rubber Company cannot be held liable for any damage caused by incorrect installation. We hereby reserve the right to change the technical information herewith without notification or prior agreement.