

 $Manufacturers \cdot Designers \cdot Distributors$








Genuine Blue Viton® Food Contact Sheeting Datasheet Product Code: RC0379

Product Description

Our blue Viton® food contact rubber is the best choice for specialist food contact and pharmaceutical applications. We produce this particular grade using an FKM A quality compound. This ensures that you get the best combination of physical properties and resistance possible.



Technical Specification

Properties	Test Method	Values
Compound	-	100% Viton FKM
Hardness (Shore A)	ASTM D2240	65° +/- 5°
Density (Specific Gravity)	ASTM D297	1.95 g/cm² +/- 5
Tensile Strength	ASTM D412	60 kg/cm²
Elongation at Break	ASTM D412	350%
Compression Set (25% 24hrs @ 70°C)	ASTM D395 Method B	40%
Polymer Content	-	100%
Working Temperature Range	-	-30°C to + 275°C
Heat Ageing (72hrs @ 150°C)		
Hardness Change	ASTM D573	+5° (Max)
Tensile Strength Change	ASTM D573	+/- 10%
Elongation at Break Change	ASTM D573	+/- 15%
Volume Swell (24hrs @ 150°C)		
IRM Oil No. 901	ASTM D 471	-6%
IRM Oil No. 902	ASTM D 471	-1%
IRM Oil No. 903	ASTM D 471	+5%

The information contained on this product information sheet is to be used as guidance. The advice is given in good faith and does not constitute any guarantee or recommendation for suitability. The Rubber Company cannot be held liable for any damage caused by incorrect installation. We hereby reserve the right to change the technical information herewith without notification or prior agreement.